

PCT/US 2004/000648
19. Nov. 2004 (19.11.2004)

PA 1237852

REC'D 29 NOV 2004

USPTO PCT

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

October 20, 2004

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/518,793

FILING DATE: November 10, 2003

PRIORITY
DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS


Trudie Wallace
Certifying Officer

Please type a plus sign (+) inside this box → PTO/SB/18 (8-00)
Approved for use through 10/31/2002. OMB 0651-0032U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1895, no persons are required to respond to a collection of information unless it displays a valid OMB control number.**PROVISIONAL APPLICATION FOR PATENT COVER SHEET**

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

INVENTOR(S)		
Given Name (first and middle [if any])	Family Name or Surname	Residence (City and either State or Foreign Country)
Thomas Richard Colin William Guy Edward	MCGEE SGARAMELLA BROWN NAISH	Nyack, NY Hoboken, NJ 5 Clandon Avenue, Engham, Surrey, England 123 Coopers Green, Bicester, Oxfordshire, England
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto		
TITLE OF THE INVENTION (280 characters max)		
APPARATUS FOR DISSEMINATING VOLATILE LIQUIDS INTO AN ATMOSPHERE		
Direct all correspondence to: CORRESPONDENCE ADDRESS		
<input checked="" type="checkbox"/> Customer Number 27,389 →		<input type="checkbox"/> Place Customer Number Bar Code Label here
OR Type Customer Number here		
<input type="checkbox"/> Firm or Individual Name		
Address		
Address		
City	State	ZIP
Country	Telephone	Fax
ENCLOSED APPLICATION PARTS (check all that apply)		
<input checked="" type="checkbox"/> Specification Number of Pages 8		<input type="checkbox"/> CD(s), Number _____
<input type="checkbox"/> Drawing(s) Number of Sheets _____		<input checked="" type="checkbox"/> Other (specify) _____
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76		<input type="checkbox"/> Certificate of Express Mailing
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)		
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees		FILING FEE AMOUNT (\$) \$160.00
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number 14-1263		
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.		
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.		
<input checked="" type="checkbox"/> No.		
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____		

Respectfully submitted,

SIGNATURE *Howard C. Lee*Date **11-10-2003**TYPED or PRINTED NAME **Howard C. Lee**REGISTRATION NO.
(if appropriate)
Docket Number:TELEPHONE **212-808-0700****48,104****102790-160****USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT**

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C.

U.S.P.T.O.
60/418793
22241
11/1003

TITLE: APPARATUS FOR DISSEMINATING VOLATILE LIQUIDS INTO AN ATMOSPHERE

EXPRESS MAIL CERTIFICATE

I hereby certify that the following items:

1. Provisional Patent Application Cover Sheet
2. Specification (8 pages)
3. Return receipt postcard

EXPRESS MAIL CERTIFICATE

I hereby certify that this paper or fee is being deposited with the United States Postal Services "Express Mail Post Office to Addressee" under "EXPRESS MAIL" Label No. EL973658067 US service under 37 CFR 1.10 on the date "indicated above and is addressed to: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450 Alexandria, VA 22313-1450 on the date indicated below.

By Michelle Mckenzie

Michella Mckenzie

Date November 10, 2003

APPARATUS FOR DISSEMINATING VOLATILE LIQUIDS INTO AN ATMOSPHERE

This invention relates to apparatus for the disseminating of volatile liquids into an atmosphere.

- 5 One very common apparatus for disseminating a volatile liquid, such as a fragrance or an insecticide, into an atmosphere consists of a porous transfer member, such as a porous wick, that is in contact with a reservoir of volatile liquid. Liquid rises up this wick and evaporates into the atmosphere. This system has drawbacks, such as the low surface area for evaporation and the tendency for the wick to fractionate complex mixtures, such as fragrances, so that some
- 10 components are disseminated earlier than others and the full effect of the fragrance is lost.

It has been proposed to overcome this disadvantage by using external capillaries, that is, capillary channels cut or moulded into a suitable substrate. One example is described in United States Patent 4,913,350, in which an external capillary channel-containing member is inserted
15 into a liquid. In another embodiment, described in copending UK Patent Application GB 0306449, there is fitted to a known transfer member a capillary sheet, that is, a sheet extending essentially perpendicularly from the transfer member and that comprises channels of capillary dimensions, to which volatile liquid can pass and travel along for evaporation. This sheet generally contacts the transfer member by means of a hole in the sheet through which the
20 transfer member protrudes and within which it fits snugly, at least some of these channels contacting the transfer member such that liquid can transfer from the member to the sheet ("liquid transfer contact").

Although this technology offers significant advantages over the porous wicks of the art, these
25 advantages have never been completely realized. It has now been found that it is possible to obtain the full benefits of the technology by adherence to certain fundamental parameters. The invention therefore provides an apparatus adapted to disseminate volatile liquid into an atmosphere from a reservoir, the transfer to atmosphere being achieved by means of a porous transfer member that transfers liquid from the reservoir to an evaporation surface, the
30 evaporation surface being a capillary sheet in liquid transfer contact with and extending

substantially transversely from the transfer member, and being further characterized in that the material of the sheet is a plastics material having a Shore D hardness of from 50 to 80 and a thickness of from 0.75 – 1.25 mm.

5 The capillary sheet and transfer member are separate components able to be put together when necessary. Typical transfer members include porous wicks of plastics, graphite and ceramics, made by any suitable method, for example, by extrusion or sintering. A preferred material is a porous plastic, such as polyester. The transfer member may be of any suitable shape or construction. Some examples of suitable configurations include

10

- the transfer member being slightly frusto-conical in shape, narrower end farthest from the reservoir; this enables a capillary sheet with a hole to be easily fitted to the transfer member;

- the provision in the transfer member of a suitable locating orifice for a capillary sheet, for example, an annular groove or a slot for a matching tab in the capillary diffusion member, to allow for easy fitting.

15 A combination of all or any of these elements may be used. In addition, other constructions that are not mentioned here but which lie within the skill of the art are also included.

20

The plastics material may be chosen for any suitable plastics material having the desired hardness properties Shore D hardness is a very well known property in the plastics industry and its measurement is common. It is a surprising feature of this invention that this parameter should have any effect on the efficacy of an evaporation surface, yet it has been found that this has a

25 marked influence. The desired Shore D hardnesses are quite soft by the standards of the plastics industry. Naturally the plastics material should also be suitably inert with respect to any of the materials in the liquid. It should also be a material that permits the formation of capillary channels by any suitable means, for example, by engraving or injection moulding. Injection

moulding is the preferred method of forming a capillary sheet. Capillary channels are typically V-shaped channels whose typical dimensions are 0.1-0.5mm wide, 0.1-0.5mm deep with the "V" angle of the channel being 10-25 degrees. The skilled person will readily appreciate what kind of plastics material is suitable for any use.

5

In a preferred embodiment of the invention, the plastics materials for use in the making of capillary sheets suitable for use in this invention have a surface energy of from 15-50 dyne/cm. The surface energy of a plastics material is dependent upon its molecular structure and is a measure of the ability of a surface to be wetted. The more inert is a plastics material chemically,

10 the lower is its surface energy. Thus, materials such as polyethylene, polypropylene and PTFE have low surface energies, whereas the plastics with more polar groups have higher surface energies. Preferably the surface energy lies in the range of from 30-45 dynes/cm.

The apparatus is generally supplied with the capillary sheet dismounted and a protective cap

15 over the porous member. The apparatus is put into service by removing the cap and placing the capillary sheet on the transfer member, such that it is in liquid transfer contact with the transfer member. This can be assured by use, for example, of one of the attachment means hereinabove described.

20 The invention is suitable for use with any volatile liquid that may be disseminated into an atmosphere by means of a porous wick. Commercial materials of this type, especially the fragrances, are generally carefully formulated proprietary compositions containing a plurality of ingredients, the precise nature of such compositions being kept confidential. However, whatever the nature of these compositions, it is a feature of this invention that they are much more 25 effectively disseminated by the apparatus according to this invention than by a wick alone.

The invention therefore additionally provides a method of disseminating a volatile liquid into an atmosphere by means of its absorption in and travel along an essentially cylindrical porous wick and then along an evaporation surface extending substantially transversely from the wick and in

30 liquid transfer contact therewith, the evaporation surface comprising a capillary sheet of a

plastics material having a Shore D hardness of from 50-80 and a thickness of from 0.75 – 1.25 mm.

The invention is further described with reference to the following non-limiting examples.

5

Example 1.

1.00 mm thick external capillary sheets were prepared from the materials in the following table and the Shore hardness measured. This was done by means of a Shore (Durometer) test

10 according to ASTM D2240 00. The apparatus used was a Mitutoyo Hardmatic HH-337-01. An indenter is pressed in the plastic and this forces the needle of the gauge round and the indicator records maximum value. This is the Shore D Hardness. The individual sheets comprised central holes that permitted them to be mounted on frusto-conical wicks by simply placing them on the wicks.

15

Trade Name	Material Type	Hardness (Measured) (Shore D)
BOREALIS* MG 9641-R	Polyethylene PE (HDPE)	56
SAN* 386R / 774	Styrene Acrylonitrile Copolymer	87
EXACT* 8210	SAN	
POLYAC* PA-758	Octene-1 Plastomer	44
IUPITAL* F40-03	Acrylonitrile-butadiene-styrene	81
LUPOY* GP5001 A-F	ABS	
IPETHENE* 320	Polyoxymethylene POM	80
RADIATER* E AX1 100	(Acetal)	
LL6201	PC/ABS	80
SCORENE* VL02020	Polyethylene PE (LDPE)	45
PS 146L	Polyethylene terephthalate	79
IUPILON* S3000	PETG	
PP 7075 L1	Polyethylene PE (LLDPE)	47
ITOCHU* H2O2	Ethylene Vinyl Acetate EVA	41
	Polystyrene PS	83
	Polycarbonate PC	84
	Polypropylene PP	55
	Polyethylene terephthalate	74

IOTEK* 8020	PETG Ionomer (sodium)	62
-------------	--------------------------	----

* Trade marks

Frusto-conical wicks of polyester (ex Micropore) were placed in a container containing a vanilla fragrance formulation used for air freshening applications (this fragrance has the advantage of being easily visible). They were allowed to equilibrate overnight. The external capillary sheets were pushed on to a frusto-conical wick until firm contact between sheet and wick (suitable to ensure liquid transfer) was made. The percentage of the capillaries in which liquid was present was assessed visually assessed after 6 minutes (0% for no transfer from wick to the capillary, 100% for the presence of liquid in all capillaries and liquid has travelled to end of all capillaries). The results are shown on the graph of Figure 1.

The graph shows that, for optimum liquid transfer, the material has to have a Shore D hardness of between 50 and 80.

15

Example 2.

Two frusto-conical wicks were placed in individual containers containing the fragrance formulation of Example 1. They were allowed to equilibrate overnight. To one of these wicks was added a polypropylene capillary sheet having a thickness of 1mm and a Shore hardness of 55, to the other an otherwise identical sheet having a thickness of 1.5mm. The percentage of each sheet wetted by the liquid is shown in the following table.

Thickness of External Capillary Sheet	% capillary sheet wetted
1.5 mm	25%
1.0 mm	100%

Hence the capillary thickness specification for direct liquid transfer as described in US 4,913,350 is not suitable for use in a hybrid wick system as it does not give optimum liquid transfer contact. The ideal thickness is 1.25 mm maximum. The lower limit of thickness is 0.75 mm set by the limit that good capillaries formed in a suitable production process such as 5 injection molding.

BEST AVAILABLE COPY

CLAIMS

1. An apparatus adapted to disseminate volatile liquid into an atmosphere from a reservoir, the transfer to atmosphere being achieved by means of a porous transfer member that transfers liquid from the reservoir to an evaporation surface, the evaporation surface being a capillary sheet in liquid transfer contact with and extending substantially transversely from the transfer member, and being further characterized in that the material of the sheet is a plastics material having a Shore D hardness of from around 50 to 80 and a thickness of from 0.75 – 1.25 mm.
- 10 2. An apparatus according to claim 1, in which the plastics materials of the capillary sheet has a surface energy of from 15-50 dyne/cm.
- 15 3. A method of disseminating a volatile liquid into an atmosphere by means of its absorption in and travel along an essentially cylindrical porous wick and then along an evaporation surface extending substantially transversely from the wick and in liquid transfer contact therewith, the evaporation surface comprising a capillary sheet of a plastics material having a Shore D hardness of from 50-80 and a thickness of from 0.75 – 1.25 mm.

ABSTRACT

- 5 An apparatus adapted to disseminate volatile liquid into an atmosphere from a reservoir, the transfer to atmosphere being achieved by means of a porous transfer member that transfers liquid from the reservoir to an evaporation surface. The evaporation surface is a capillary sheet substantially transversely from the transfer member, and being further characterized in that the material of the sheet is a plastics material having a Shore D hardness of from around 50 to 80
- 10 and a thickness of from 0.75 – 1.25 mm. These sheets make especially good liquid transfer contact with the transfer member.